

PRODUCT DATA SHEET

DESCRIPTION:

Penetron Plus is a unique integral crystalline chemical treatment for the waterproofing and protection of concrete. Penetron Plus has been specially formulated for dry-shake applications on horizontal concrete surfaces where greater impact and abrasion resistance is required. Packaged in the form of a dry powder compound, Penetron Plus consists of Portland cement, various active proprietary chemicals, and a synthetic aggregate hardener that has been crushed and graded to particle sizes suitable for concrete floors. Penetron Plus becomes an integral part of the concrete surface thereby eliminating problems normally associated with coatings (e.g. scaling, dusting, flaking and delamination). The active chemicals react with the moisture in the fresh concrete causing a catalytic reaction, which generates a non-soluble crystalline formation within the pores and capillary tracts of the concrete.

RECOMMENDED FOR:

- ◆ Sewage and Water Treatment Plants
- ◆ Traffic Bearing Surfaces
- ◆ Warehouse Floors
- ◆ Foundation Slabs
- ◆ Below-grade
- ◆ Parking Structures

ADVANTAGES:

- ◆ Resists extreme hydrostatic pressure from either positive or negative surface of the concrete slab
- ◆ Becomes an integral part of the substrate
- ◆ Highly resistant to aggressive chemicals
- ◆ Can seal hairline cracks up to 1/64" (0.4mm)
- ◆ Allows concrete to breath
- ◆ Non-toxic. Approved for use in potable water applications (NSF 61)
- ◆ Less costly to apply than most other methods
- ◆ Permanent
- ◆ Increases flexibility in the construction schedule

PACKAGING:

This product can be purchased in 40 lb (18 kg) bags or 55 lb (25 kg) pails.

STORAGE:

Penetron products must be stored dry at a minimum temperature of 45° F (7°C). Shelf life is one year when stored under proper conditions.

DIRECTIONS FOR USE:

Coverage:

Under normal conditions, the coverage rate for Penetron Plus is 1 lb per SY (0.5 kg per m²), depending on the degree of abrasion resistance required.

Note: Under heavy traffic conditions or where even greater abrasion resistance is required, consult a Penetron Technical Representative for a recommendation that meets your specific needs.

Application Procedures:

1. Fresh concrete is placed, consolidated and leveled.
2. Wait until concrete can be walked on leaving an indentation of 1/4"–1/3" (6.5mm – 9.5mm). Concrete should be free of bleed water and be able to support the weight of a power trowel. Then, float open the surface.
3. Immediately after floating open the surface, apply one-half of the dry shake material by hand or mechanical spreader. The dry shake material must be spread evenly.
4. As soon as the dry shake material has absorbed moisture from the base slab, it should be power floated to the surface.
5. Immediately after power floating, apply remaining dry shake material at right angles to the first application.
6. Allow remaining dry shake material to absorb moisture from the base slab and then power float the material into the surface.
7. When concrete has hardened sufficiently, power trowel surface to the required finish.

PRODUCT DATA SHEET

Curing:

Curing is important and should begin as soon as final set has occurred but before surface starts to dry. Conventional moist curing procedures such as water spray, wet burlap or plastic covers may be used. Curing should continue for at least 48 hours. In hot, dry sunny conditions consult manufacturer for specific instructions. In lieu of moist curing, concrete sealers and curing compounds meeting ASTM C-309 may be used.

Note: It is common that edges of a slab wall will set up earlier than the main body of concrete. Such edge areas can be dry-shaked and finished with hand tools prior to proceeding with application of the main body of concrete.

For the best results when applying dry shake materials, the air content of the concrete should not exceed 3% (a high air content can make it difficult to achieve a proper application). If a high entrained air content is specified (e.g. for concrete that will be exposed to freezing and thawing), contact the Technical Department of Penetron International Ltd. for further application information.

In hot, dry, or windy conditions, it is advisable to use an evaporation retardant on the fresh concrete surface to prevent premature drying of the slab.

Chronic moving cracks or joints will require a suitable flexible sealant.

For certain concrete mix designs, we recommend a test panel be produced and evaluated for finishing. (For example, high performance concrete with a low water/cement ratio, air entrainment, super plasticizers, or silica fume may reduce bleed water and make the concrete more difficult to finish).

Technical Services:

For more instructions, alternative application methods, or information concerning the compatibility of the Penetron treatment with

other products or technologies, contact the Technical Department of Penetron International Ltd. or your local Penetron representative.

HEALTH AND SAFETY:

Penetron Plus is alkaline. As a cementitious powder or mixture, Penetron Plus may cause significant skin and eye irritation. Directions for treating these problems are clearly detailed on all Penetron pails and packaging. Comprehensive and up-to-date Material Safety Data Sheets are maintained on all Penetron products. Each sheet contains health and safety information for the protection of your employees and customers. Contact ICS Penetron International Ltd. or your local Penetron representative to obtain copies of Material Safety Data Sheets prior to product storage or use.

WARRANTY:

ICS PENETRON INTERNATIONAL LTD. warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to ICS PENETRON INTERNATIONAL LTD. shall be limited to replacement of the material proven to be defective and shall in no case be liable otherwise or for incidental or consequential damages.

ICS PENETRON INTERNATIONAL LTD. MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED.

User shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith.